

**PAT-NO:** JP02000154336A  
**DOCUMENT-IDENTIFIER:** JP 2000154336 A  
**TITLE:** PRIMER COMPOSITION AND BONDING OR COATING METHOD  
**PUBN-DATE:** June 6, 2000

**INVENTOR-INFORMATION:**

NAME	COUNTRY
TAGUCHI, KOICHI	N/A
SUDO, HIROSHI	N/A

**ASSIGNEE-INFORMATION:**

NAME	COUNTRY
DENKI KAGAKU KOGYO KK	N/A

**APPL-NO:** JP10330696  
**APPL-DATE:** November 20, 1998

**INT-CL (IPC):** C09D005/00 , C08J007/04 , C09D004/02 , C09J005/02

**ABSTRACT:**

**PROBLEM TO BE SOLVED:** To obtain a primer composition capable of improving adhesiveness and adhesion when bonding or coating a metal with a radically polymerizable curing resin by making the composition include a specific phosphoric ester (salt) and an acrylic monomer.

**SOLUTION:** This composition is obtained by including (A) an acid phosphoric ester (salt) represented by the formula  $[R \text{ is } CH_2=CR_1CO(OR_2)_m \text{ [} R_1 \text{ is H or } CH_3; R_2 \text{ is } C_2H_4, C_3H_6, C_4H_8 \text{ or the like; (m) is 1-10]; (n) \text{ is 1 or 2}]$  (e.g. acid phosphoxyethyl methacrylate) in an amount of preferably 0.1-30 pts.wt., more preferably 0.5-10 pts.wt. based on 100 pts.wt. of the sum total of the components A and B and (B) an acrylic monomer [e.g. methyl (meth)acrylate] in an amount of preferably 70-99.9 pts.wt., more preferably 90-99.5 pts.wt. based on 100 pts.wt. of the sum total of the components A and B preferably without including a volatile solvent or water.

**COPYRIGHT:** (C)2000,JPO